

SeptimA Salvia



COLOUR

Light grey

Product description

The bricks are formed individually in the unsanded mould to a solid mass, pressed from clay of alluvial origin from an area located in the Scheldt basin and fired in a tunnel oven at a temperature of approximately 1180°C. On the narrow side the bricks have an unsanded surface structure.

TECHNICAL CHARACTERISTICS

The paving is laid in fired clay bricks of Belgian origin, quality class A, carrying the Benor mark, the CE mark and UKCA mark.

CE label according to EN 1344 : 2013 / AC : 2015

Manufacturing dimensions (L x W x H) : *218x52x72 mm

Quantity / m² with a traditional joint : ca. 85

PHYSICAL AND MECHANICAL PROPERTIES ACCORDING TO EN 1344: 2013 / AC: 2015

| Aspect | Class | Mean | Individual |
|----------------------------|-------|-------------------------|-------------------------|
| Water absorption NBN EN771 | W3 | Max 3% | Max 4% |
| Transverse breaking load | T4 | Min 80 N/mm | Min 64 N/mm |
| Abrasion resistance | A3 | Max 450 mm ³ | Max 500 mm ³ |
| Frost resistance | FP100 | freeze/thaw resistant | freeze/thaw resistant |
| Wet skid resistance | U3 | >55 | |
| Acid resistance | C | < 7% | |
| Size tolerance | R1 | Max. ± 0,4 √d | Max. 0,6 √d |

SeptimA Salvia

Productshot



VANDE MOORTELE
CLAY PAVERS • FACING BRICKS • SLIPS

ORIGIN : VANDE MOORTELE NV | Scheldekant 5 | BE-9700 OUDENAARDE |
T +32 (0)55 33 55 66 | BTW BE 0432.038.790 | -info@vandemoortel-bricksandpavers.com